



Europäisches Patentamt  
European Patent Office  
Office européen des brevets



(11) **EP 0 891 995 A1**

(12) **EUROPEAN PATENT APPLICATION**

(43) Date of publication:  
20.01.1999 Bulletin 1999/03

(51) Int. Cl.<sup>6</sup>: **C08F 214/22**

(21) Application number: **98113399.4**

(22) Date of filing: **17.07.1998**

(84) Designated Contracting States:  
**AT BE CH CY DE DK ES FI FR GB GR IE IT LI LU  
MC NL PT SE**  
Designated Extension States:  
**AL LT LV MK RO SI**

(30) Priority: **18.07.1997 JP 209863/97**

(71) Applicant:  
**Nippon Mektron, Limited  
Minato-ku Tokyo (JP)**

(72) Inventors:  
• **Saito, Satoru**  
Kitaibaraki City, Ibaraki (JP)  
• **Tatsu, Haruyoshi**  
Hitachi City, Ibaraki (JP)

(74) Representative:  
**Hansen, Bernd, Dr. Dipl.-Chem. et al**  
**Hoffmann Eitle,**  
**Patent- und Rechtsanwälte,**  
**Arabellastrasse 4**  
**81925 München (DE)**

(54) **Process for producing fluorine-containing elastomer**

(57) Fluorine-containing elastomers produced through copolymerization reaction of vinylidene fluoride, tetrafluoroethylene, perfluoro(lower alkyl vinyl ether) and chlorotrifluoroethylene in the presence of a bromine-containing monomer compound and an iodine- and bromine-containing compound, where hexafluoropropene can be further copolymerized, have not only a distinguished resistance to amine-based additives and also distinguished low-temperature characteristic and engine oil resistance, and also a lower cost attained by reduced copolymer proportion of perfluoro(lower alkyl vinyl ether).

EP 0 891 995 A1

## Description

## BACKGROUND OF THE INVENTION

## 1. FIELD OF THE INVENTION

The present invention relates to a process for producing a fluorine-containing elastomer, and more particularly to a process for producing a fluorine-containing elastomer having a good resistance to an amine-based additive.

## 2. DESCRIPTION OF RELATED ART

Fluorine-containing elastomers have distinguished heat resistance, chemical resistance and compression set resistance characteristic, and thus have been so far used in many fields including automobile parts. With recent trends of higher performance and lower fuel consumption for automobile engines, a higher performance is required for the engine oil. To this effect a large amount of an amine-based additive is often added to the engine oil. Thus, the fluorine-containing elastomers to be used as materials for automobile parts in contact with the engine oil requires an amine-based additive resistance.

Vinylidene fluoride-hexafluoropropene copolymers and vinylidene fluoride-hexafluoropropene-tetrafluoroethylene terpolymers are widely used as fluorine-containing elastomers, but the vulcanisation products of these fluorine-containing elastomers undergo surface hardening and deterioration by engine oils and thus are not suitable for application to parts in contact with engine oils. It seems that the vinylidene fluoride-hexafluoropropene linking sites in the polymer main chain react with the amine-based additive to cause hardening.

Several fluorine-containing elastomers with an improved resistance to the amine-based additive are known on the other hand.

- Tetrafluoroethylene-perfluoro(methyl vinyl ether) copolymers show a distinguished resistance not only to the amine-based compounds, but also to various polar solvents, but have poor low-temperature characteristics, such as glass transition point (Tg) as low as about -5° to about 0°C and are more expensive than the above-mentioned, widely used fluorine-containing elastomers.
- Tetrafluoroethylene-propylene copolymers show a good resistance to amine-based compounds and various polar solvents, but have a TR-10 as an indicator of low-temperature characteristics of 10°C and are inferior to low-temperature characteristics compared with the above-mentioned, widely used fluorine-containing elastomers.
- Vinylidene fluoride-propylene-tetrafluoroethylene terpolymers or vinylidene fluoride- $\alpha$ -olefin-hexafluoropropene-tetrafluoroethylene quaternary copolymers have a somewhat improved low-temperature characteristic (TR-10: -8°C), though not satisfactory, and cannot be used as molding materials for the dynamic sealing due to a poor wear resistance.
- Vinylidene fluoride-tetrafluoroethylene-perfluoro(methyl vinyl ether) terpolymers have distinguished resistance to amine-based additives and low-temperature characteristic (TR-10: -30°C), but have such a problem as several times higher cost than those of the above-mentioned, widely used fluorine-containing elastomers, because of the inevitable copolymerization of about 15 to about 25% by mole of expensive perfluoro(methyl vinyl ether).

## SUMMARY OF THE INVENTION

An object of the present invention is to provide a process for producing a fluorine-containing elastomer having not only a distinguished resistance to amine-based additives, but also distinguished low-temperature characteristic and engine oil resistance at a lower cost by reducing a copolymerization proportion of perfluoro(lower alkyl vinyl ether).

Such an object of the present invention can be attained by producing a fluorine-containing elastomer through copolymerization reaction of vinylidene fluoride, tetrafluoroethylene, perfluoro(lower alkyl vinyl ether) having a lower alkyl group having 1 to 3 carbon atoms and chlorotrifluoroethylene in the presence of a bromine-containing monomer compound and an iodine- and bromine-containing compound, where hexafluoropropene can be further copolymerized.

## DETAILED DESCRIPTION OF THE INVENTION

Fluorine-containing elastomers obtained according to the present process have a copolymer composition comprising about 50 to about 85% by mole, preferably about 60 to about 80% by mole, of vinylidene fluoride; about 5 to about 30% by mole, preferably about 5 to about 20% by mole, of tetrafluoroethylene; about 2 to about 15% by mole of perfluoro(lower alkyl vinyl ether) having a perfluoro lower alkyl group having 1 to 3 carbon atoms, such as perfluoro(methyl vinyl ether), perfluoro(ethyl vinyl ether), perfluoro(propyl vinyl ether), etc.; and about 2 to about 20% by mole, preferably

about 5 to about 15% by mole, of chlorotrifluoroethylene, where not more than 10% by mole, preferably not more than about 5% by mole, of hexafluoropropene may be further copolymerized, sum total being 100% by mole.

When the copolymerization proportion of vinylidene fluoride is less than about 50% by mole, the low-temperature characteristic will be deteriorated, whereas above about 85% by mole the chemical resistance and elasticity will be lowered. When the copolymerization proportion of tetrafluoroethylene is less than about 5% by mole, the heat resistance and chemical resistance will be lowered, whereas above about 30% by mole the low-temperature characteristic will be deteriorated. When the copolymerization proportion of perfluoro(lower alkyl vinyl ether) is less than about 2% by mole, the low-temperature characteristic and chemical resistance will be lowered, whereas copolymerization proportion above about 15% by mole is not preferable from the viewpoint of cost. Furthermore, when the copolymerization proportion to chlorotrifluoroethylene is less than about 2% by mole, no desired cost-down effect can be obtained, whereas above about 20% by mole the low-temperature characteristic will be deteriorated. In case of further copolymerization of hexafluoropropene, the oil resistance can be improved, but when the copolymerization proportion of hexafluoropropene is above about 10% by mole, the resistance to amine-based additives will be lowered.

The present fluorine-containing elastomers can be further copolymerized with fluorinated olefins, various olefin compounds or vinyl compounds to such a proportion as not to inhibit the copolymerization reaction or deteriorate the physical properties of vulcanization products (e.g. not more than about 20% by mole on the basis of the elastomer) mainly to reduce the cost. Fluorinated olefins for use in the present invention include, for example, monofluoroethylene, trifluoroethylene, trifluoropropylene, pentafluoropropylene, hexafluoroisobutylene, dichlorodifluoroethylene, etc. Olefin compounds and vinyl compounds for use in the present invention include, for example, ethylene, propylene, 1-butene, isobutylene, methyl vinyl ether, ethyl vinyl ether, butyl vinyl ether, cyclohexyl vinyl ether, vinyl acetate, vinyl propionate, vinyl chloride, vinylidene chloride, trifluorostyrene, etc. among which at least one of trifluoroethylene, methyl vinyl ether, etc. can be preferably used.

Copolymerization reaction can be carried out according to any polymerisation method, for example, by emulsion polymerization, suspension polymerization, solution polymerization, bulk polymerization, etc., among which the emulsion polymerization method is preferable from a higher polymerization degree and the economical viewpoints. The emulsion polymerisation reaction can be carried out generally at a temperature of about 20 to about 80°C under a pressure of about 0 to about 20 kg/cm<sup>2</sup> gauge, using a water-soluble inorganic peroxide such as ammonium persulfate, etc. or its redox system as a catalyst and also using an emulsifier such as ammonium perfluorooctanoate, ammonium perfluoroheptanoate and ammonium perfluorononanoate or their mixture, preferably ammonium perfluorooctanoate. To adjust pH in the polymerisation system a buffering electrolyte such as phosphates (Na<sub>2</sub>HPO<sub>4</sub>, NaH<sub>2</sub>PO<sub>4</sub>, KH<sub>2</sub>PO<sub>4</sub>, etc.) or borates (Na<sub>2</sub>B<sub>4</sub>O<sub>7</sub>, etc.), or NaOH can be also used.

The copolymerisation reaction is carried out in the presence of a bromine-containing monomer compound and an iodine- and bromine-containing compound, preferably an iodine- and bromine-containing bromine compound represented by the following general formula:



where R is a fluorocarbon group, a chlorofluorocarbon group, a chlorohydrocarbon group or a hydrocarbon group, and n and m each are 1 or 2.

Bromine-containing monomer compound to be used for forming cross-linking sites includes, for example, brominated vinyl compounds or brominated olefins having 2 to 10 carbon atoms, preferably 2 to 5 carbon atoms, such as vinyl bromide, 1-bromo-2,2-difluoroethylene, perfluoroallyl bromide, 4-bromo-1,1,2-trifluorobutene, 4-bromo-3,3,4,4-tetrafluorobutene, 4-bromo-1,1,3,3,4,4-hexafluorobutene, bromotrifluoroethylene, 4-bromo-3-chloro-1,1,3,4,4-pentafluorobutene, 6-bromo-5,5,6,6-tetrafluorohexene, 4-bromoperfluorobutene-1, 3,3-difluoroallyl bromide, etc., among which 1-bromo-2,2-difluoroethylene is preferably used.

About 0.001 to about 5% by mole, preferably about 0.01 to about 3% by mole, more preferably about 0.1 to about 3% by mole, of the bromine-containing monomer compound can be used on the basis of total of the above-mentioned 4 kinds or 5 kinds of comonomers for constituting the fluorine-containing elastomer. Below about 0.001% by mole the compression set resistance characteristic of the resulting vulcanisation products will be deteriorated, whereas above about 5% by mole elongation of the resulting vulcanization products will be lowered.

Iodine- and bromine-containing bromine compound represented by the general formula RBnIm, (where R, m and n have the same meanings as defined above) acts as a chain transfer agent to adjust the molecular weight, thereby improving the processability.

The iodine- and bromine-containing compound represented by the said general formula is selected from those which cannot lose the effects through side reactions under polymerization conditions, wherein R is selected from fluorohydrocarbon groups, chlorofluorohydrocarbon groups, chlorohydrocarbon groups or hydrocarbon groups generally having 1 to 10 carbon atoms, and each of the groups may have a functional group such as -O-, -S-, =NR, -COOH, -SO<sub>2</sub>, -SO<sub>3</sub>H, -PO<sub>3</sub>H, etc.

Such iodine- and bromine-containing compound may be a saturated or unsaturated linear or aromatic compound, wherein n and m each are preferably 1. The iodine and bromine-containing compound where at least one of n and m is 2 produces a fluorine-containing elastomer of three-dimensional structure, and thus is desirable to use within such a range as not to deteriorate the processability.

The linear iodine- and bromine-containing compound includes, for example, 1-bromo-2-iodoperfluoroethane, 1-bromo-3-iodo-perfluoropropane, 1-bromo-4-iodoperfluorobutane, 2-bromo-3-iodoperfluorobutane, 1-bromo-2-iodoperfluoro(2-methylpropane), monobromomonoiodoperfluorocyclobutane, monobromomonoiodoperfluoropentane, monobromomonoiodoperfluoro-n-octane, monobromomonoiodoperfluorocyclohexane, 1-bromo-1-iodo-2-chloroperfluoroethane, 1-bromo-2-iodo-2-chloroperfluoroethane, 1-iodo-2-bromo-2-chloroperfluoroethane, 1,1-dibromo-2-iodoperfluoroethane, 1,2-dibromo-2-iodoperfluoroethane, 1,2-diiodo-2-bromoperfluoroethane, 1-bromo-2-iodo-1,2,2-trifluoroethane, 1-iodo-2-bromo-1, 2,2-trifluoroethane, 1-bromo-2-iodo-1,1-difluoroethane, 1-iodo-2-bromo-1,1-difluoroethane, 1-bromo-2-iodo-1-fluoroethane, 1-iodo-2-bromo-1-fluoroethane, 1-bromo-2-iodo-1,1,3,3,3-pentafluoropropane, 1-iodo-2-bromo-1,1,3,3,3-pentafluoropropane, 1-bromo-2-iodo-3,3,4,4,4-pentafluorobutane, 1-iodo-2-bromo-3,3,4,4,4-pentafluorobutane, 1,4-dibromo-2-iodoperfluorobutane, 2,4-dibromo-1-iodoperfluorobutane, 1,4-diiodo-2-bromoperfluorobutane, 1,4-dibromo-2-iodo-3,3,4,4-tetrafluorobutane, 1,4-diiodo-2-bromo-3,3,4,4-tetrafluorobutane, 1,1-dibromo-2,4-diiodoperfluorobutane, 1-bromo-2-iodo-1-chloroethane, 1-iodo-2-bromo-1-chloroethane, 1-bromo-2-iodo-2-chloroethane, 1-bromo-2-iodo-1,1-dichloroethane, 1,3-dibromo-2-iodoperfluoropropane, 2,3-dibromo-2-iodoperfluoropropane, 1,3-diiodo-2-bromoperfluoropropane, 1-bromo-2-iodoethane, 1-bromo-2-iodopropane, 1-iodo-2-bromopropane, 1-bromo-2-iodobutane, 1-iodo-2-bromobutane, 1-bromo-2-iodo-2-trifluoromethyl-3,3,3-trifluoropropane, 1-iodo-2-bromo-2-trifluoromethyl-3,3,3-trifluoropropane, 1-bromo-2-iodo-2-phenylperfluoroethane, 1-iodo-2-bromo-2-phenylperfluoroethane, 3-bromo-4-iodoperfluorobutene-1, 3-iodo-4-bromoperfluorobutene-1, 1-bromo-4-iodoperfluorobutene-1, 1-iodo-4-bromoperfluorobutene-1, 3-bromo-4-iodo-3,4,4-trifluorobutene-1, 4-bromo-3-iodo-3,4,4-trifluorobutene-1, 3-bromo-4-iodo-1,1,2-trifluorobutene-1, 4-bromo-5-iodoperfluoropentene-1, 4-iodo-5-bromoperfluoropentene-1, 4-bromo-5-iodo-1,1,2-trifluoropentene-1, 4-iodo-5-bromo-1,1,2-trifluoropentene-1, 1-bromo-2-iodoperfluoroethyl perfluoromethyl ether, 1-bromo-2-iodoperfluoroethyl perfluoroethyl ether, 1-bromo-2-iodoperfluoroethyl perfluoropropyl ether, 2-bromo-3-iodoperfluoropropyl perfluorovinyl ether, 1-bromo-2-iodoperfluoroethyl perfluorovinyl ether, 1-bromo-2-iodoperfluoroethyl perfluoroallyl ether, 1-bromo-2-iodoperfluoroethyl methyl ether, 1-iodo-2-bromoperfluoroethyl methyl ether, 1-iodo-2-bromoethyl ethyl ether, 1-bromo-2-iodoethyl 2'-chloroethyl ether, etc. These iodine and bromine-containing compounds can be prepared according to an appropriate, known process; for example, a monobromomonoiodo, fluorine-containing olefin can be obtained by allowing a fluorine-containing olefin to react with iodine bromide.

The aromatic, iodine- and bromine-containing compound includes, for example, benzenes having a substituent group such as 1-iodo-2-bromo, 1-iodo-3-bromo, 1-iodo-4-bromo, 3,5-dibromo-1-iodo, 3,5-diiodo-1-bromo, 1-(2-iodoethyl)-4-(2-bromoethyl), 1-(2-iodoethyl)-3-(2-bromoethyl), 1-(2-iodoethyl)-4-(2-bromoethyl), 3,5-bis(2-bromoethyl)-1-(2-iodoethyl), 3,5-bis(2-iodoethyl)-1-(2-bromoethyl), 1-(3-iodopropyl)-2-(3-bromo-propyl), 1-(3-iodopropyl)-3-(3-bromopropyl), 1-(3-iodopropyl)-4-(3-bromopropyl), 3,5-bis(3-bromopropyl)-1-(3-iodopropyl), 1-(4-iodobutyl)-3-(4-bromobutyl), 1-(4-iodobutyl)-4-(4-bromo-butyl), 3,5-bis(4-iodobutyl)-1-(4-bromobutyl), 1-(2-iodoethyl)-3-(3-bromopropyl), 1-(3-iodopropyl)-3-(4-bromobutyl), 3,5-bis(3-bromopropyl)-1-(2-iodoethyl), 1-iodo-3-(2-bromoethyl), 1-iodo-3-(3-bromopropyl), 1,3-diiodo-5-(2-bromoethyl), 1,3-diiodo-5-(3-bromopropyl), 1-bromo-3-(2-iodoethyl), 1-bromo-3-(3-iodopropyl), 1,3-dibromo-5-(2-iodoethyl), 1,3-dibromo-5-(3-iodopropyl), etc. and perfluorobenzenes having a substituent group such as 1-iodo-2-bromo, 1-iodo-3-bromo, 1-iodo-4-bromo, 3,5-dibromo-1-iodo, 3,5-diiodo-1-bromo, etc.

During the polymerization reaction, the iodine and bromine of these iodine- and bromine-containing compounds readily undergo radical cleavage under the action of an organic peroxide radical-generating source, and the monomers undergo addition growth reaction owing to the high reactivity of the generated radicals, and then the reaction is discontinued by withdrawing the iodine and bromine from the iodine- and bromine-containing compound to give a fluorine containing elastomer having iodine and bromine at the molecule terminals. The iodine atom and bromine atom bonded to the molecule terminals also act as cross-linking sites for the peroxide vulcanization.

The iodine- and bromine-containing compound is bonded to the fluorine-containing elastomer so that not more than about 5 % by weight, generally about 0.001 to about 5% by weight, preferably about 0.01 to about 3% by weight in terms of iodine and bromine each may be contained in the resulting fluorine-containing elastomer.

The present fluorine-containing elastomer has a  $\eta_{sp}/c$  value of about 0.1 to about 2 dl/g, preferably about 0.2 to about 1.5 dl/g as measured at 35°C in methyl ethyl ketone and can be cured by so far well known various vulcanisation methods, for example, by peroxide vulcanisation using an organic peroxide, polyamine vulcanization using a polyamine compound or a polyol vulcanization using a polyhydroxy compound, or by irradiation of radiation rays, electron beam, etc. Among them, peroxide vulcanization is particularly preferable, because the cured elastomer can give vulcanization products showing good resistances to basic substances such as amines, etc. or to nucleophilic substances.

The organic peroxide for use in the peroxide vulcanization includes, for example, 2,5-dimethyl-2,5-bis(tert-butylperoxy)hexane, 2,5-dimethyl-2,5-bis(tert-butylperoxy)hexane-3, benzoyl peroxide, bis (2,4-dichlorobenzoyl) peroxide,

dicumyl peroxide, di-tert-butyl peroxide, tert-butyl cumyl peroxide, tert-butylperoxybenzene, 1,1-bis(tert-butylperoxy)-3,5,5-trimethyl cyclohexane, 2,5-dimethylhexane-2,5-dihydroperoxide,  $\alpha,\omega'$ -bis(tert-butylperoxy)-p-diisopropylbenzene, 2,5-dimethyl-2,5-di(benzoylperoxy)hexane, tert-butylperoxy isopropyl carbonate etc.

In the peroxide vulcanization using the organic peroxide, a polyfunctional, unsaturated compound, such as tri(meth)allyl isocyanulate, tri(meth)allyl cyanulate, triallyl trimellitate, N,N'-m-phenylene bismaleimide, diallyl phthalate, tris(diallylamine)-s-triazine, triallyl phosphite, 1,2-polybutadiene, ethyleneglycol diacrylate, diethyleneglycol diacrylate, etc. can be usually used as a cocross-linking agent to obtain more distinguished vulcanization characteristics, mechanical strength and compression set.

The foregoing additive components to the peroxide vulcanisation system are used in the following amounts: the organic peroxide is used in an amount of generally about 0.1 to about 10 parts by weight, preferably about 0.5 to about 5 parts by weight per 100 parts by weight of the fluorine-containing elastomer, and the cocross-linking agent is used in an amount of generally about 0.1 to about 10 parts by weight, preferably about 0.5 to about 5 parts by weight and a cross-linking aid is used in an amount of not more than about 15 parts by weight per 100 parts by weight of the fluorine-containing elastomer.

Furthermore, an inorganic filler such as carbon black, silica, etc.; an acid acceptor such as ZnO, CaO, Ca(OH)<sub>2</sub>, MgO, PbO, synthetic hydrotalcite, etc; various pigments: a processing aid such as polyethyleneglycol monomethyl ether, Crown ether, etc. ; a plasticizer such as RfO[OCF(CF<sub>3</sub>)CF<sub>2</sub>O]<sub>n</sub>Rf', RfO[CF(CF<sub>3</sub>)CF<sub>2</sub>O]<sub>p</sub>(CF<sub>2</sub>CF<sub>2</sub>O)<sub>q</sub>(CF<sub>2</sub>O)<sub>r</sub>Rf', RfO(CF<sub>2</sub>CF<sub>2</sub>O)<sub>n</sub>(CF<sub>2</sub>O)<sub>m</sub>Rf', RfO(CF<sub>2</sub>CF<sub>2</sub>CF<sub>2</sub>O)<sub>n</sub>Rf', where Rf and Rf' each are a perfluoroalkyl group, a perfluoro-alkyleneether triazine oligomer having -(CFXOCF<sub>2</sub>)<sub>a</sub>(CF<sub>2</sub>)<sub>b</sub>(CF<sub>2</sub>OCFX)<sub>c</sub>- in the molecule, where X is F or a CF<sub>3</sub> group (see JP-A-7-285948); a stabilizer, and other necessary additives can be appropriately added to the composition containing the above-mentioned components.

The present fluorine-containing elastomer can be further blended or cocross-linked with other substance having a peroxide cross-linkability such as silicone oil, silicone rubber, fluorosilicone rubber, fluorophosphazene rubber, ethylene-vinyl acetate copolymer, ethylene-acrylic acid ester copolymer, ethylene-propylene(-diene) copolymer rubber, acrylonitrile-butadiene copolymer rubber, acrylic acid ester rubber, etc.

The present composition can be prepared by kneading through rolls, a kneader, a Bambury mixer, etc. , and its crosslinking is carried out by heating at about 140 to about 220°C for about 5 to about 60 minutes. If required, secondary vulcanization is carried out preferably in air or in an inert atmosphere such as a nitrogen gas atmosphere at about 150 to about 250°C for about 5 to about 50 hours.

The present fluorine-containing elastomer shows a distinguished chemical resistance, particularly to amine-based additives contained in engine oil, etc. , and also has distinguished low-temperature characteristic, heat resistance and compression set resistance characteristics. A distinguished cost performance can be obtained by reducing the copolymerization proportion of expensive perfluoro(lower alkyl vinyl ether).

Furthermore, it is noted that chlorotrifluoroethylene so far presumed to promote reaction with amines is effective for improving the amine resistance and additive oil resistance contrary to the expectation.

#### PREFERRED EMBODIMENTS OF THE INVENTION

The present invention will be described below, referring to Examples.

#### EXAMPLE 1

The following compounds were charged into a stainless steel autoclave having a capacity of 10L, after flushed with a nitrogen gas and then evacuated:

Ammonium perfluorooctanoate	15. 4g
Sodium hydroxide	2. 2g
Disodium hydrogen phosphate	11. 0g
Distilled water	3, 360ml

After the autoclave was flushed again and evacuated, a monomer mixture consisting of the following compounds was charged therein:

Vinylidene fluoride [VdF]	820g (70 mol. %)
Tetrafluoroethylene [TFE]	180g (10 mol. %)
Perfluoro(methyl vinyl ether) [FMVE]	300g (10 mol. %)
Chlorotrifluoroethylene [CTFE]	210g (10 mol. %)

The autoclave inside temperature was elevated to 50°C, and then the following compounds were charged therein to initiate polymerization reaction:

1-Bromo-2-iodotetrafluoroethylene	7.0g
1,1-Difluoro-2-bromoethylene	7.0g
Ammonium persulfate	1.5g

The reaction was continued for 20 hours and then the residual gas was purged therefrom to interrupt the reaction. 5.0 Kg of the resulting aqueous latex was salted out with an aqueous sodium chloride solution, and dried to obtain 1.4 Kg of white fluorine-containing elastomer A (polymerization yield: 93%).

It was found by <sup>19</sup>F-NMR analysis that the resulting fluorine-containing elastomer had a copolymer composition in a molar ratio of VdF/TFE/FMVE/CTFE=65/15/8/12 and its  $\eta_{sp}/c$  value was 1.1 dl/g.

#### EXAMPLE 2

In Example 1, a monomer mixture having the following charge amounts was used, whereby 1.3 Kg of white fluorine-containing elastomer B having the following copolymer composition in molar ratio was obtained with  $\eta_{sp}/c=1.0$  dl/g (polymerization yield: 88%):

	<u>Charge amounts</u>	<u>Copolymer composition</u>
VdF	820g (70 mol. %)	69 mol. %
TFE	180g (10 mol. %)	14 mol. %
FMVE	150g ( 5 mol. %)	3 mol. %
CTFE	320g (15 mol. %)	14 mol. %

#### EXAMPLE 3

In Example 1, a monomer mixture having the following charge amounts (HFP: hexafluoropropene) was used, whereby 1.4 Kg of white fluorine-containing elastomer C having the following copolymer composition in molar ratio was obtained with  $\eta_{sp}/c=0.9$  dl/g (polymerization yield: 93%):

	<u>Charge amounts</u>	<u>Copolymer composition</u>
5	VdF 820g (70 mol. %)	70 mol. %
	TFE 180g (10 mol. %)	12 mol. %
	FMVE 150g ( 5 mol. %)	4 mol. %
10	HFE 140g ( 5 mol. %)	6 mol. %
	CTFE 210g (10 mol. %)	8 mol. %

#### 15 COMPARATIVE EXAMPLE 1

The following compounds were charged into a stainless steel autoclave having a capacity of 10L after flushed with a nitrogen gas and then evacuated:

20	Ammonium perfluorooctanoate	30g
	Disodium hydrogen phosphate	10g
25	Distilled water	5L

30 After the autoclave was flushed again with a nitrogen gas and the evacuated, a monomer mixture having the following initial charge amounts described hereinafter was charged therein at the initial stage.

After the autoclave inside temperature was elevated to 70°C, the following compounds were charged therein to initiate polymerization reaction:

35	1, 1-Difluoro-2-iodotetrafluoroethylene	10g
	1-Bromo-2-iodotetrafluoroethane	9g
	Ammonium persulfate	7g

40

With progress of polymerization reaction, the autoclave inside pressure was lowered, and when the pressure reached to 3.3 MPa, the monomer mixture was additionally charged to make the pressure to 3.4 MPa. After repetition of polymerization pressure decrease to 3.3 MPa and increase to 3.4 MPa, the monomer mixture was additionally charged therein in the total charge amounts described hereinafter within the period of 90 minutes.

45 After the final additional charge of the monomer mixture, polymerization reaction was continued for further one hour, and then the unreacted gas was purged therefrom, whereby 7.4 Kg of an aqueous latex was obtained. The aqueous latex so obtained was salted out with an aqueous sodium chloride solution and dried. whereby 2.9 Kg of white fluorine-containing elastomer D having the following copolymer composition in molar ratio was obtained with  
 50  $\eta_{sp}/c=0.95\text{dl/g}$  (polymerization yield: 81%):

55

		<u>Initial charge amounts</u>	<u>Total additional charge amounts</u>	<u>Copolymer composition</u>
5	VdF	210g	350g	65 mol. %
	TFE	510g	850g	17 mol. %
10	HFP	940g	700g	18 mol. %

## 15 COMPARATIVE EXAMPLE 2

In Example 1, a monomer composition having the following charge amounts was used. From 5.1 Kg of the resulting aqueous latex was obtained 1.55 Kg of white fluorine-containing elastomer E having the following copolymer composition in molar ratio was obtained with  $\eta_{sp}/c=0.85\text{dl/g}$  (polymerization yield: 96%):

		<u>Charge amounts</u>	<u>Copolymer composition</u>
20	VdF	820g (70 mol. %)	71 mol. %
25	TFE	180g (10 mol. %)	11 mol. %
	FMVE	610g (20 mol. %)	18 mol. %



## REFERENCE EXAMPLES 1 TO 5

5	Fluorine-containing elastomer A (Ref. Ex. 1)	100 parts by weight
	" B (Ref. Ex. 2)	100 "
	" C (Ref. Ex. 3)	100 "
10	" D (Ref. Ex. 4)	100 "
	" E (Ref. Ex. 5)	100 "
15	MT Carbon black	30 "
	Zinc oxide	6 "
	Triallyl isocyanurate	4 "
20	Organic peroxide (Luperco 101XL, trademark of a product commercially available from Atochem-Yoshitomi Pharmaceutical Industries Ltd., Japan)	3 "

The foregoing components were kneaded in a two-roll mill, and the resulting kneading products were subjected to press vulcanization (primary vulcanization) at 180°C for 10 minutes and oven vulcanization (secondary vulcanization) at 200°C for 22 hours. The resulting vulcanization products were determined for the following properties:

30	Normal state physical properties:	according to DIN 53505 and 53504
	Thermal degradation test:	measurements of changes in normal state physical properties at 230°C after 70 hours
	Compression set:	according to ASTM D-395 Method B
35	Low-temperature characteristic:	evaluated as TR-10
	Engine oil resistance:	measurement of changes in normal state physical properties, elongation at surface crack generation and percent volume swelling when dipped in Toyota castle motor oil green SG 10W-30 at 175°C for 70 hours
40	Resistance to amine-based additive:	measurement of changes in normal state physical properties, elongation at surface crack generation and percent volume swelling when dipped in 1% benzylamine-mixed JIS No. 3 oil at 175°C for 70 hours

## REFERENCE EXAMPLE 6

5	Fluorine-containing elastomer F(Aflas 200, trademark of a product commercially available from Asahi Glass Co., Ltd., Japan)	100 parts by weight
	MT carbon black	30 "
10	Calcium stearate	1 "
	Triallyl isocyanurate	4 "
15	Organic peroxide (Peroxydon F40, trademark of a product commercially available from NOF Corp., Japan)	3 "

20 The foregoing components were kneaded in a two-roll mill and the resulting kneading product was subjected to press vulcanization at 170°C for 20 minutes and oven vulcanization at 230°C for 22 hours. The resulting vulcanization product was determined for the properties in the same manner as in Reference Examples 1 to 5.

Results are shown in the following Table.

25

30

35

40

45

50

55

Table

		Reference Example No.					
		1	2	3	4	5	6
5							
	[Normal state physical properties]						
10	Hardness (Shore A) (pts)	72	73	71	69	70	70
	100% Modulus (MPa)	6.0	7.5	6.5	5.8	6.8	7.5
	Strength at break (MPa)	23.8	20.7	20.0	21.3	21.0	17.1
15	Elongation at break (%)	210	200	220	280	220	190
	[Thermal degradation test]						
20	Hardness change (pts)	-1	-1	-1	0	0	+1
	100% Modulus change ratio (%)	+2	+5	+5	-2	+3	+1
25							
	Change ratio of strength at break (%)	-8	-10	-5	-1	-7	-3
30	Change ratio of elongation at break (%)	+5	+10	+10	+5	-5	+5
	[Compression set]						
	200°C, 70 hr (%)	24	26	26	36	26	30
35	[Low-temperature characteristic]						
	TR-10 (°C)	-26	-23	-24	-17	-30	-8
40	[Engine oil resistance]						
	Hardness change (pts)	+2	+2	+2	+3	+1	+1
	100% Modulus change ratio (%)	+15	+15	+25	+16	+10	+5
45	Change ratio of strength at break (%)	-27	-30	-30	-50	-45	-35
	Change ratio of elongation at break (%)	-33	-35	-40	-50	-40	-30
50	Elongation at surface crack generation (%)	60	50	40	10	60	80
55							

	Percent volume swelling	(%)	+0.9	+1.0	+1.0	+1.1	+1.0	+4.5
5	[Resistance to amine-based additive]							
	Hardness change	(pts)	+1	+1	+1	+2	+1	-2
10	100% Modulus change ratio	(%)	+12	+15	+15	+25	+5	+11
	Change ratio of strength at break	(%)	-15	-17	-15	-20	-10	-6
15	Change ratio of elongation at break	(%)	-10	-10	-15	-30	-10	-7
20	Elongation at surface crack generation	(%)	100	90	70	20	100	130
	Percent volume swelling	(%)	+3.3	+3.8	+3.5	+4.3	+3.4	+10.7

## Claims

1. A process for producing a fluorine-containing elastomer, which comprises subjecting vinylidene fluoride, tetrafluoroethylene, perfluoro(lower alkyl vinyl ether) having a lower alkyl group of 1 to 3 carbon atoms and chlorotrifluoroethylene to copolymerization reaction in the presence of a bromine-containing monomer compound and an iodine- and bromine-containing compound.
2. A process according to Claim 1, wherein the bromine-containing monomer compound is a boromated vinyl compound of 2 to 10 carbon atoms.
3. A process according to Claim 1, wherein the bromine-containing monomer compound is a brominated olefin of 2 to 10 carbon atoms.
4. A process according to anyone of the claims 1 to 3, wherein the iodine- and bromine-containing compound is a compound represented by the following general formula:



wherein R is a fluorohydrocarbon group, a chlorofluorohydrocarbon group, a chlorohydrocarbon group or a hydrocarbon group, and n and m each are 1 or 2.

5. A process according to anyone of the claims 1 to 4, wherein hexafluoropropene is further subjected to the copolymerization reaction.
6. A fluorine-containing elastomer having a copolymer composition comprising 50 to 85% by mole of vinylidene fluoride, 5 to 30% by mole of tetrafluoroethylene, 2 to 15% by mole of perfluoro(lower alkyl vinyl ether) having a lower alkyl group of 1 to 3 carbon atoms and 2 to 20% by mole of chlorotrifluoroethylene, produced by subjecting vinylidene fluoride, tetrafluoroethylene, perfluoro(lower alkyl vinyl ether) having a lower alkyl group of 1 to 3 carbon atoms and chlorotrifluoroethylene to copolymerization reaction in the presence of a bromine-containing monomer compound and an iodine- and bromine-containing elastomer.

7. A fluorine-containing elastomer according to Claim 6, wherein 0.1 to 3% by mole of a bromine-containing monomer compound is further copolymerized on the basis of 4 kinds of comonomers constituting the fluorine-containing elastomer.

5 8. A fluorine-containing elastomer according to Claim 6 or 7 wherein not more than 10% by mole of hexafluoropropene is further copolymerized.

9. A fluorine-containing elastomer according to Claim 8, wherein 0.1 to 3% by mole of a bromine-containing monomer compound is further copolymerized on the basis of 5 kinds of comonomers constituting the fluorine-containing elastomer.

15

20

25

30

35

40

45

50

55



European Patent  
Office

# EUROPEAN SEARCH REPORT

Application Number  
EP 98 11 3399

DOCUMENTS CONSIDERED TO BE RELEVANT			
Category	Citation of document with indication, where appropriate, of relevant passages	Relevant to claim	CLASSIFICATION OF THE APPLICATION (Int.Cl.6)
P,X	EP 0 834 521 A (NIPPON MEKTRON KK) 8 April 1998 * abstract; claims; examples * * page 3, line 23 - line 27 *	1-9	C08F214/22
X	US 5 225 504 A (TATSU HARUYOSHI ET AL) 6 July 1993 * abstract; claims; examples * * column 6, line 24 - line 32 *	1-9	
X	US 4 943 622 A (NARAKI AKIHIRO ET AL) 24 July 1990 * abstract; claims; examples * * column 5, line 14 - line 25 *	1-9	
The present search report has been drawn up for all claims			TECHNICAL FIELDS SEARCHED (Int.Cl.6)
			C08F
Place of search <b>THE HAGUE</b>		Date of completion of the search <b>21 October 1998</b>	Examiner <b>Mettler, R-M</b>
<p>CATEGORY OF CITED DOCUMENTS</p> <p>X : particularly relevant if taken alone Y : particularly relevant if combined with another document of the same category A : technological background O : non-written disclosure P : intermediate document</p> <p>T : theory or principle underlying the invention E : earlier patent document, but published on, or after the filing date D : document cited in the application L : document cited for other reasons &amp; : member of the same patent family, corresponding document</p>			

EPO FORM 1503 03 82 (P04C01)